



**PPG** *IdeaScapes*.<sup>™</sup> Integrated products, people and services to inspire your design and color vision.

PPG IdeaScapes Guide Specification –
Coil and Extrusion Coatings, Liquid and Powder Coating Systems

SECTION 050513 - SHOP-APPLIED COATINGS FOR METAL

**SECTION 05080 - FACTORY-APPLIED METAL COATINGS** 

Revised February 2014

For latest updates please visit <a href="www.ppgideascapes.com">www.ppgideascapes.com</a>
To speak with an architectural service representative, call PPG's Architect Hotline 888-774-4332/888-PPG-IDEA

To view Specifier Notes in Microsoft Office XP, Office 2000: TOOLS/OPTIONS/VIEW/HIDDEN TEXT To print Specifier Notes in Microsoft Office XP, Office 2000: FILE/PRINT/OPTIONS/HIDDEN TEXT

To view Specifier Notes with Microsoft Word 2007, OFFICE BUTTON/ WORD OPTIONS/DISPLAY/ HIDDEN TEXT To print Specifier Notes in Microsoft Word 2007, OFFICE BUTTON/ WORD OPTIONS/DISPLAY/ PRINT HIDDEN TEXT

# [SECTION 050513 - SHOP-APPLIED COATINGS FOR METAL]

# [SECTION 05080 - FACTORY-APPLIED METAL COATINGS]

## PART 1 - GENERAL

### 1.1 SUMMARY

## A. Section Includes:

1. Shop-applied coatings for architectural metals.

#### B. Related Sections:

- 1. Division 01 Section "Sustainable Design Requirements".
- 2. Division 05 Section "Pipe and Tube Railings".
- Division 05 Section "Decorative Metal".
- 4. Division 05 Section "Decorative Metal Railings".
- 5. Division 05 Section "Decorative Formed Metal".
- 6. Division 07 Section "Metal Roof Panels".
- 7. Division 07 Section "Metal Wall Panels".
- 8. Division 07 Section "Sheet Metal Roofing".
- 9. Division 07 Section "Sheet Metal Flashing and Trim".
- 10. Division 07 Section "Roof Specialties".
- 11. Division 08 Section "Overhead Coiling Doors".
- 12. Division 08 Section "Overhead Coiling Grilles".
- 13. Division 08 Section "Aluminum-Framed Entrances and Storefronts".
- 14. Division 08 Section "All-Glass Entrances and Storefronts".
- 15. Division 08 Section "Automatic Entrances".
- 16. Division 08 Section "Revolving Door Entrances".
- 17. Division 08 Section "Glazed Aluminum Curtain Walls".
- 18. Division 08 Section "Structural-Sealant-Glazed Curtain Walls".
- 19. Division 08 Section "Aluminum Windows".
- 20. Division 08 Section "Metal-Framed Skylights".
- 21. Division 08 Section "Louvers And Vents".
- 22. Division 10 Section "Metal Lockers".
- 23. Division 13 Section "Metal Building Systems".
- 24. Division 08 Section "Louvers And Vents".

## 1.2 REFERENCES

- A. American Architectural Manufacturers Association (AAMA):
  - AAMA 621 Voluntary Specification for High Performance Organic Coatings on Coil Coated Architectural Hot Dipped Galvanized (HDG) and Zinc-Aluminum Coated Steel Substrates.

- 2. AAMA 2603 Voluntary Specification, Performance Requirements and Test Procedures for Pigmented Organic Coatings on Aluminum Extrusions and Panels
- 3. AAMA 2604 Voluntary Specification, Performance Requirements and Test Procedures for High Performance Organic Coatings on Aluminum Extrusions.
- 4. AAMA 2605 Voluntary Specification, Performance Requirements and Test Procedures for Superior Performing Organic Coatings on Aluminum Extrusions.

# B. ASTM International (ASTM):

- 1. ASTM B 117 Practice for Operating Salt Spray (Fog) Apparatus.
- 2. ASTM G 85 annex 5 Modified Salt Spray Cyclic Fog Test
- 3. ASTM D 7901 Standard Test Method for Nondestructive Measurement of Dry Film Thickness of Nonconductive Coatings Applied to a Nonferrous Metal Base.
- 4. ASTM D 1654 Standard Test Method for Evaluation of Painted or Coated Specimens Subjected to Corrosive Environments.
- ASTM D 2244 Test Method for Calculation of Color Differences from Instrumentally Measured Color Coordinates.
- 6. ASTM D 2247 Standard Practice for Testing Water Resistance of Coatings in 100% Relative Humidity.
- 7. ASTM D 3363 Standard Test Method for Film Hardness by Pencil Test.
- 8. ASTM D 4214 Test Methods for Evaluating Degree of Chalking of Exterior Paint Films.
- 9. ASTM E 1980 Practice for Calculating Solar Reflectance Index of Horizontal and Low-Sloped Opaque Surfaces.
- C. U.S. Green Building Council (USGBC): LEED Green Building Rating System, NC (New Construction). Version 2.2.

# 1.3 PERFORMANCE REQUIREMENTS

- A. Solar Reflective Index: Provide metal roof panel coatings with solar reflectance index of not less than 78 for slopes of 2:12 or less and 29 for slopes greater than 2:12, per ASTM E 1980.
- B. Energy Star Compliance: Provide metal roof panel coatings identical to those listed on U.S Department of Energy's ENERGY STAR Roof Products Qualified Product List.
- C. CEC-Title 24 Compliance: Provide metal roof panel coatings with initial solar reflectance not less than [0.70] and emissivity not less than [0.75] per CRRC-1.

#### 1.4 SUBMITTALS

A. Product Data: For each type of coating product specified.

## B. LEED Submittals:

- 1. Product Test Reports for Credit SS 7.2: For metal roof panel coatings to document compliance with solar reflectance index requirement.
- C. Samples for Selection: For each color, gloss specified.
- D. Samples for Verification: For each coating product, for each color, gloss, and texture specified, on specified substrate.
- E. Product test reports.

- F. Qualifications: For shop-applied coatings Applicator.
- G. Maintenance data.
- H. Warranty: Sample of special warranty.

## 1.5 QUALITY ASSURANCE

A. Applicator Qualifications: Coating manufacturer's [approved] [certified] Applicator who is equipped, trained and approved for application of coatings required for this Project, and is approved to provide warranty specified in this Section.

# 1.6 DELIVERY, STORAGE, AND HANDLING

- A. Deliver, unload, and store shop-coated items so that they remain free of damage or deformation. Package and protect items during shipping and handling. Protect stored items from water; stack to facilitate drainage. Keep shop-coated items out of contact with materials that may adversely affect the coating.
- B. Protect shop-coated items with protective covering until installed.

## 1.7 COORDINATION

A. Coordinate submittal and selection procedures for items to receive shop-applied coatings. Where items are indicated to match coatings selected for other items, adjust formulations as required to achieve match. Submit samples for verification indicating compliance with matching requirements.

#### 1.8 WARRANTY

- A. Coating Warranty: Coating Applicator's warranty in which Applicator agrees to repair finish or replace coated items that demonstrate deterioration of shop-applied finishes within warranty period indicated.
  - 1. Exposed Coating: Deterioration includes but is not limited to:
    - a. Color fading in excess of 5 Delta E Hunter units per ASTM D 2244.
    - b. Peeling, checking, or cracking of coating adhesion to metal.
    - c. Chalking in excess of a No. 8 per ASTM D 4214, when tested per Method D 659.
    - d. Corrosion of substrate in excess of a No. 6 on cut edges and a No. 8 on field surfaces, when measured per ASTM D 1654.
  - 2. Warranty Period: [10] [20] [25] [30] years from date of Substantial Completion.

# PART 2 - PRODUCTS

## 2.1 MANUFACTURERS

A. Basis-of-Design Product: Provide shop-applied coatings manufactured by PPG Industries, Inc., Pittsburgh, PA, (888) 774-4332, Email: <a href="mailto:ideascapes@ppg.com">ideascapes@ppg.com</a>; Website: <a href="www.ppgideascapes.com">www.ppgideascapes.com</a> [ or comparable products of another manufacturer approved by Architect prior to bid].

#### 2.2 APPROVED COATING APPLICATORS

- A. Acceptable Applicators: Provide shop-applied coatings applied by one of the following [manufacturer-approved] [manufacturer-certified] applicators:
  - 1. < Insert list of acceptable applicators>.

#### 2.3 HIGH-PERFORMANCE ORGANIC FINISH MATERIALS - EXTRUSIONS

- A. Liquid Fluoropolymer Aluminum Extrusion Coatings, AAMA 2605: Minimum 70 percent PVDF resin, by weight, in color coat [and clear topcoat].
  - 1. Product: PPG Industries, Inc., [Duranar] [Duranar Sunstorm] [Duranar XL].
  - 2. Pencil Hardness, ASTM D 3363: F, minimum.
  - 3. Salt Spray Resistance ASTM G 85 2,000 hours
  - 4. Humidity ASTM D 2247 1,000 hours
  - 5. Dry Film Thickness, ASTM D 1400: 0.20mil primer coat plus 1.0 mil color coat, 1.20 mil total, minimum thickness.
  - 6. Dry Film Thickness, ASTM D 1400: 0.20 mil primer coat plus [1.0 mil barrier coat,] 1.0 mil color coat and 0.4 mil clear topcoat, [1.6 mil] [2.6 mil] total, minimum thickness.
- B. Liquid Fluoropolymer Aluminum Extrusion Coatings, AAMA 2604: 50% PVDF resin, by weight, in color coat.
  - 1. Product: **PPG Industries, Inc., Acrynar**
  - 2. Pencil Hardness. ASTM D 3363: F. minimum.
  - 3. Salt Spray Resistance ASTM B117
  - 4. Humidity
  - 5. Dry Film Thickness, ASTM D 7901: 0.20 mil primer coat plus 1.0 mil color coat, 1.2 mil total, minimum thickness.

## 2.4 POWDER COATING MATERIALS - EXTRUSIONS

- A. Powder Coatings, Fluoropolymer, meeting performance requirements of AAMA 2605:
  - 1. Product: **PPG Industries, Inc., Duranar Powder Coating**.
  - 2. Pencil Hardness, ASTM D 3363: F, minimum.
  - 3. Salt Spray Resistance, ASTM G 85: 2,000 hours.
  - 4. Humidity Resistance, ASTM D 2247: 4,000 hours.
  - 5. Dry Film Thickness, ASTM D 7901: 0.20-0.30 mil primer coat plus 1.5 to 2.5 mil Duranar Powder Topcoat, 1.7 mil total, minimum thickness.

- B. Powder Coatings, Fluoropolymer, meeting performance requirements of AAMA 2605:
  - 1. Product: **PPG Industries, Inc., Coraflon Powder Coating**.
  - 2. Pencil Hardness, ASTM D 3363: F, minimum.
  - 3. Salt Spray Resistance, ASTM G 85: 2,000 hours.
  - 4. Humidity Resistance, ASTM D 2247: 4,000 hours.
  - 5. Dry Film Thickness, ASTM D 7901: [2.0] mil, minimum thickness.
- C. Powder Coatings, Polyester, meeting performance requirements of AAMA 2604.
  - 1. Product: PPG Industries, Inc., Envirocron 04 Ultra-Durable Powder Coating.
  - 2. Pencil Hardness. ASTM D 3363: H 2H.
  - 3. Salt Spray Resistance, ASTM B 117: 3,000 hours.
  - 4. Humidity Resistance, ASTM D 2247: 3,000 hours.
  - 5. Dry Film Thickness, ASTM D 7901: [2.0] mil, minimum thickness.

## 2.5 HIGH-PERFORMANCE ORGANIC FINISH MATERIALS – COIL COATINGS

- A. Liquid Fluoropolymer Aluminum Sheet Coil Coatings, AAMA 2605: 70 percent PVDF resin, by weight, in color coat [and clear topcoat].
  - 1. Product: PPG Industries, Inc., [Duranar] [Duranar Sunstorm] [Duranar XL] [Duranar Plus] [Duranar XL Plus] [Duranar ULTRA-Cool].
  - 2. Pencil Hardness, ASTM D 3363: HB H.
  - 3. Salt Spray Resistance, ASTM G 85: 1,000 hours.
  - 4. Humidity Resistance, ASTM D 2247: 1,000 hours.
  - 5. Dry Film Thickness, ASTM D 7901: 0.15 mil primer coat plus 0.70 mil color coat, 0.85 mil total, minimum thickness.
  - 6. Dry Film Thickness, ASTM D 7901: 0.15 mil primer coat plus [0.70 mil barrier coat,] 0.70 mil color coat and 0.45 mil clear topcoat, [1.25 mil] [2.0 mil] total, minimum thickness.
  - 7. Dry Film Thickness, ASTM D 7901: 0.80 mil primer coat plus 0.80 mil color coat, 1.60 mil total, minimum thickness.
  - 8. Dry Film Thickness, ASTM D 7901: 0.80 mil primer coat plus 0.80 mil color coat and 0.80 clear topcoat, 2.40 mil total, minimum thickness.
- B. Liquid Fluoropolymer Aluminum Sheet Coil Coatings, AAMA 2605: FEVE resin,[clear topcoat].
  - 1. Product: **PPG Industries, Inc., Coraflon XL.**
  - 2. Pencil Hardness. ASTM D 3363: HB H.
  - 3. Salt Spray Resistance, ASTM G 85: 3,000 hours.
  - 4. Humidity Resistance, ASTM D 2247: 3,000 hours.
  - 5. Dry Film Thickness, ASTM D 7901: 0.6 mil clear coat
- C. Liquid Fluoropolymer Steel Sheet Coil Coatings, AAMA 621: Minimum 70 percent PVDF resin, by weight, in color coat [and clear topcoat].
  - 1. Product: PPG Industries, Inc., [Duranar] [Duranar Sunstorm] [Duranar XL] [Duranar Plus] [Duranar XL Plus] [Duranar ULTRA-Cool].
  - 2. Pencil Hardness, ASTM D 3363: HB H.
  - 3. Salt Spray Resistance, ASTM B 117: 1,000 hours.
  - 4. Humidity Resistance, ASTM D 2247: 1,000 hours.
  - 5. Dry Film Thickness, ASTM D 7901: 0.15 mil primer coat plus 0.70 mil color coat, 0.85 mil total, minimum thickness.

- 6. Dry Film Thickness, ASTM D 7901: 0.15 mil primer coat plus [0.70 mil barrier coat,] 0.70 mil color coat and 0.45 mil clear topcoat, [1.25 mil] [2.0 mil] total, minimum thickness.
- 7. Dry Film Thickness, ASTM D 7901: 0.80 mil primer coat plus 0.80 mil color coat, 1.60 mil total, minimum thickness.
- 8. Dry Film Thickness, ASTM D 7901: 0.80 mil primer coat plus 0.80 mil color coat and 0.80 clear topcoat, 2.40 mil total, minimum thickness.
- D. Liquid Fluoropolymer Steel Sheet Coil Coatings, AAMA 621: FEVE resin, [clear topcoat].
  - 1. Product: PPG Industries, Inc., Coraflon XL.
  - 2. Pencil Hardness, ASTM D 3363: HB H.
  - 3. Salt Spray Resistance, ASTM B 117: 1,000 hours.
  - 4. Humidity Resistance, ASTM D 2247: 1,000 hours.
  - 5. Dry Film Thickness, ASTM D 7901: 0.6 mil clear coat

## 2.6 INTERIOR ORGANIC FINISHING MATERIALS – EXTRUSION

- A. Liquid acrylic and polyester one coat finishes meeting AAMA 2603
  - 1) Product: PPG Industries., [Duracron] [Polycron]
  - 2) Pencil Hardness H minimum
  - 3) Salt Spray Resistance, ASTM B117: 1500 hours
  - 4) Humidity Resistance, ASTM D2247: 1500 hours
  - 5) Dry Film Thickness, ASTM D1400: 1.0 mil +/- 0.2 mil
- B. Powder polyester one coat finish meeting AAMA 2603
  - 1) Product: **PPG Industries.**, **Envirocron 03**
  - 2) Pencil Hardness: H minimum
  - 3) Salt Spray Resistance, ASTM B117: 1500 hours
  - 4) Humidity Resistance, ASTMD2247: 1500 hours
  - 5) Dry Film Thickness, ASTM1400: 2.5 mils +/- 0.5

# 2.7 INTERIOR ORGANIC FINISHING MATERAILS - COIL

- A. Liquid acrylic one coat finish
  - 1) Product: **PPG Industries**., **Duracron**
  - 2) Pencil Hardness: HB-H
  - 3) Salt Spray Resistance, ASTM B117: 1,000 hours
  - 4) Humidity resistance, ASTM D2247: 1,000 hours
  - 5) Dry Film Thickness, ASTM D1005: 0.75-0.85 mils

# 2.8 FINISHES

- A. Pretreatment: Mechanically clean and chemically pretreat fabricated items in accordance with coating manufacturer's requirements and AAMA requirements for finish indicated.
- B. Application: Apply primer and finish coats in accordance with coating manufacturer's requirements for finish indicated.

## 2.9 SHOP-APPLIED COATINGS SCHEDULE

- A. High-Performance Organic Finish for Aluminum Extruded Items: [2-coat] [3-coat] fluoropolymer finish: [AAMA 2604] [AAMA 2605].
  - Coated Items: <Insert list of extruded items to receive high-performance organic finish>.
  - 2. Color: [Match custom sample] [As selected from manufacturer's full range] [As designated or scheduled] <Insert color>.
  - 3. Gloss: [Low, less than 20] [Medium, 20 79] [High, 80 and above] [As selected from manufacturer's full range] [As designated or scheduled].
- B. High-Performance Organic Finish for Aluminum Sheet Items: [2-coat] [3-coat] fluoropolymer finish: AAMA 2605.
  - Coated Items: <Insert list of extruded items to receive high-performance organic finish>.
  - 2. Color: [Match custom sample] [As selected from manufacturer's full range] [As designated or scheduled] < Insert color>.
  - 3. Gloss: [Low, less than 20] [Medium, 20 79] [High, 80 and above] [As selected from manufacturer's full range] [As designated or scheduled].
  - 4. Concealed/ Backer Finish: Pretreat substrate and apply coating applicator's standard acrylic, polyester or epoxy finish in accordance with manufacturers' requirements.
- C. High-Performance Organic Finish for Steel Sheet Items: [2-coat] [3-coat] fluoropolymer finish: AAMA 621.
  - Coated Items: <Insert list of extruded items to receive high-performance organic finish>.
  - 2. Color: [Match custom sample] [As selected from manufacturer's full range] [As designated or scheduled] <Insert color>.
  - 3. Gloss: [Low, less than 20] [Medium, 20 79] [High, 80 and above] [As selected from manufacturer's full range] [As designated or scheduled].
  - 4. Concealed/ Backer Finish: Pretreat substrate and apply coating applicator's standard acrylic, polyester or epoxy finish in accordance with manufacturers' requirements.
- D. Powder-Coat Finish for [Aluminum Extruded Items] AAMA [2604] [2605] [and] [Steel Items Fabricated from Shapes and Plates]:
  - Coated Items: <Insert list of extruded items to receive high-performance organic finish>.
  - 2. Color: [Match custom sample] [As selected from manufacturer's full range] [As designated or scheduled] <Insert color>.
  - 3. Gloss: [Low, less than 20] [Medium, 20 79] [High, 80 and above] [As selected from manufacturer's full range] [As designated or scheduled].
  - 4. Surface: [Smooth] [Rough texture, glossy surface] [Fine texture] [As selected from manufacturer's full range] [As designated or scheduled].

# PART 3 - EXECUTION

# 3.1 INSTALLATION

A. Refer to individual specifications sections for installation requirements for items receiving shop-applied coatings.

# 3.2 PROTECTION

A. Remove protective wrap from coated items at time of installation.

[END OF SECTION 05 05 13]

[END OF SECTION 05080]